

IsolTech™ Wall & Ceiling System

Typical chemical-resistance characteristics for

KEY E - Excellent
 G-Good
 L - Limited
 U - Unsuitable

	72°F	140°F		72°F	140°F
	ISOLTECH™			ISOLTECH™	
Acetic Acid 0-10%	E	E	Kerosene	E	E
Acetic Acid 10-20%	E	E	Lacquer Thinners	L	U
Acetic Acid 20-30%	E	G	Methyl Alcohol	E	E
Acetic Acid 30-60%	E	E	Methyl Chloride	U	U
Acetic Acid 80%	G	L	Methyl Ethyl Ketone	U	U
Acetic Acid - Glacial	G	U	Naptha	E	E
Acetic Acid Vapors	E	E	Nitric Acid 10%	E	G
Acetylene	E	E	Nitric Acid 20%	E	L
Aluminum Chloride	E	E	Nitric Acid 35%	E	G
Aluminum Fluoride	E	E	Nitric Acid 40%	E	G
Aluminum Hydroxide	E	E	Nitric Acid 60%	E	L
Aluminum Nitrate	E	E	Perchloric Acid 10%	E	L
Ammonia - Dry Gas	E	E	Perchloric Acid 70%	E	U
Ammonia - Liquid	L	U	Photographic Chemicals	E	E
Ammonium Bifluoride	E	E	Potassium Perchlorite	E	E
Ammonium Carbonate	E	E	Potassium Permanganate 10%	E	E
Ammonium Thiocyanate	E	E	Propyl Alcohol	E	E
Anthraquinone	E	E	Sodium Antimonate	E	E
Asphalt	E	E	Sodium Arsenite	E	E
Barium Hydroxide	E	E	Sodium Benzoate	E	G
Benzene	U	U	Sodium Ferrocyanide	E	E
Bleach - 12.5% Active CL	E	G	Sodium Fluoride	E	E
Boric Acid	E	E	Sodium Thiosulfate (Hypo)	E	E
Bromic Acid	E	E	Tannic Acid	E	E
Calcium Bisulfite	E	E	Toluol or Toluene	U	U
Calcium Hypochlorite	E	E	Trichloroethylene	U	U
Ethylene Dichloride	U	U	Triethanolamine	E	G
Ethylene Glycol	E	E	Trimethyl Propane	E	G
Fatty Acids	E	E	Turpentine	E	E
Fish Solubles	E	E	Urea	E	E
Formaldehyde	E	E	Urine	E	E
Fuel Oil (containing H SO)	E	E	Vinegar	E	E
Gas - Natural (Dry)	E	E	White Gasoline	E	E
Gas - Natural (Wet)	E	E	Zinc Chloride	E	E
Glycolic Acid 30%	E	E	Zinc Cyanide	E	E
Isopropyl Alcohol	E	E			

For chemicals not listed above:
 Architectural floor systems, inc,
 206 Campus Drive , Arlington Heights, IL 60004
 800-323-6792